

EOS Copper Cu
for EOS M 290

EOS Copper Cu

EOS M 290 | 20 μm

High purity copper for EOS M 290 platform to reach good electrical and thermal conductivity. Suitable for a wide variety of applications.



Main Characteristics

- High purity copper
- Good electrical and heat conductivity
- Process developed to achieve best possible conductivity using the EOS M 290

Typical Applications

- Heat exchangers
- Electronics
- Variety of industry applications requiring good conductivity

Headquarters

EOS GmbH
Electro Optical Systems
Robert-Stirling-Ring 1
D-82152 Krailling/Munich
Germany
Phone +49 89 893 36-0
info@eos.info

www.eos.info

in EOS
 EOSGmbH
 EOS.global
 EOSGmbH
 #ShapingFuture

Further Offices

EOS France
Phone +33 437 497 676

EOS Greater China
Phone +86 21 602 307 00

EOS India
Phone +91 443 964 8000

EOS Italy
Phone +39 023 340 1659

EOS Japan
Phone +81 45 670 0250

EOS Korea
Phone +82 2 6330 5800

EOS Nordic Et Baltic
Phone +46 31 760 4640

EOS of North America
Phone +1 877 388 7916

EOS Singapore
Phone +65 6430 0463

EOS UK
Phone +44 1926 675 110


Product Information

Current TRL	3
DMLS System	EOS M 290
Material	EOS Copper Cu
Process	Cu_020_CoreM291_100

Layer thickness 20 μm

Volume rate 1.7 mm³/s

Porosity < 5 %*



* depending on job load and part geometry

Typical part properties

Typical part properties	Yield strength Rp _{0.2} [MPa]	Tensile strength Rm [MPa]	Elongation at break A [%]
Mechanical properties as manufactured	180	200	5
Mechanical properties heat treated	140	190	20
Conductivity as manufactured	> 80 % IACS (tested acc. ASTM E1004-17)		
Conductivity heat treated	> 90 % IACS (tested acc. ASTM E1004-17)		

Copper can be heat treated to reach different mechanical properties and conductivity values. Properties in the table have been achieved with following heat-treatment:

Hold 1 h at ~ 1,000 °C in argon atmosphere, slow cooling with argon

Copper and its alloys have high conductivity; hence high power is required for processing. The achieved density, which influences the mechanical properties, is typical for a 400 W laser. Please refer to the application notes for EOS Copper products for further information.

Status 11/2019

EOS is certified according to ISO 9001. EOS®, DMLS® and EOSPRINT® are registered trademarks of EOS GmbH in some countries. For more information visit www.eos.info/trademarks.

The quoted values refer to the use of this material with above specified type of EOS DMLS system, EOSYSTEM and EOSPRINT software version, parameter set and operation in compliance with parameter sheet and operating instructions. Part properties are measured with specified measurement methods using defined test geometries and procedures. Further details of the test procedures used by EOS are available on request. Any deviation from these standard settings may affect the measured properties. The data correspond to EOS knowledge and experience at the time of publication and they are subject to change without notice as part of EOS' continuous development and improvement processes. EOS does not warrant any properties or fitness for a specific purpose, unless explicitly agreed upon. This also applies regarding any rights of protection as well as laws and regulations.

